



Transport
Roads & Maritime
Services

Test method T403

Loss on ignition

OCTOBER 2012



Revision Summary

Ed/Rev Number	Clause Number	Description of Revision	Authorisation	Date
		Reformatted and Revision Summary Added	D.Dash	May 1999
		Date on Test Method Revised to Agree with Date on Revision Summary	D.Dash	Feb 2001
Ed 2/ Rev 0	All	Reformatted RMS template	J Friedrich	October 2012

Note that Roads and Maritime Services is hereafter referred to as 'RMS'.

The most recent revision to Test method T403 (other than minor editorial changes) are indicated by a vertical line in the margin as shown here.

Test method T403

Loss on ignition

1. Scope

This test method sets out the procedure to be used to determine the loss on ignition of materials such as Portland Cement and Fly Ash.

2. TEST REQUIREMENTS, PROCEDURE AND REPORTING

The procedure is identical with the method described in Australian Standard 2350.2 and is similar to that described in Australian Standard 1129, except that:

- (i) Platinum crucible 20-30 mL capacity fitted with cover shall be used for Portland Cement and similar materials.
- (ii) Porcelain crucible 20-30 mL capacity fitted with cover shall be used for Fly Ash and similar materials.